



Polypropylene HE125MO

Polypropylene Homopolymer for Injection Moulding

Description

HE125MO is a polypropylene homopolymer intended for injection moulding characterised by good flow properties combined with high stiffness.

Due to its formulation **HE125MO** is specially suitable for high speed injection moulding of articles demanding easy flow. **HE125MO** has got very good organoleptic properties and can be used with any masterbatch without discolouring problems.

Applications

HE125MO is a general-purpose material that can be used in the following applications:

- Houseware and thin wall packaging.
- Articles with rather long and narrow flow lengths.

Physical Properties**

		Typical Value*	Unit	Test Method
Density		908	kg/m ³	ISO 1183
Melt Flow Rate	(230°C/2.16kg)	12	g/10 min	ISO 1133
Tensile Stress at Yield	(50 mm/min)	34.5	MPa	ISO 527-2
Tensile Strain at Yield	(50 mm/min)	9	%	ISO 527-2
Tensile Modulus	(1 mm/min)	1550	MPa	ISO 527-2
Charpy Impact Strength, notched	(+23°C)	3.5	kJ/m ²	ISO 179/1eA
Hardness, Rockwell		100	R-scale	ISO 2039-2
Heat Deflection Temperature	(0.45 N/mm ²)	88	°C	ISO 75-2

* Data should not be used for specification work

** Values determined on injection moulded specimens acc. to ISO 1873-2 (97), based on 7 days conditioning time.

Processing Guidelines

The grade can be processed on standard injection moulding machines. Following moulding parameters should be used as guidelines.

Melt temperature	220 – 260°C
Injection speed	Very high
Holding pressure	Minimum required to avoid sink marks (typical values are 200 - 500 bars)
Mould temperature	20 – 40°C
Shrinkage	1 - 2%, depending on wall thickness and moulding parameters.

Borealis A/S

Parallelsvej 16
DK-2800 Kongens Lyngby (Denmark)
Telephone: +45 45 96 60 00
Fax : +45 45 96 61 23
www.borealisgroup.com



Polypropylene HE125MO

Storage and Handling

The product should be stored in dry conditions at temperatures below 50°C and protected from UV-light.

Improper storage can initiate degradation, which results in odour generation and colour changes and can have negative effects on the physical properties of the product.

Safety

HE125MO is not classified as dangerous preparation.

Dust and fines from the product carry a risk of dust explosion. All equipment should be properly earthed. Inhalation of dust should be avoided as it may cause irritation of the respiratory system. Small amounts of fumes are generated during processing of the product. Proper ventilation is therefore required.

Recycling

The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.

A Safety Data Sheet is available on request. Please contact your Borealis representative for more details on various aspects of safety, recovery and disposal of the product.

Related Documents

The following related documents are available on request, and represent various aspects on the usability, safety, recovery and disposal of the product:

Recovery and disposal of Polyolefins
Information on Emissions from Processing and Fires
Safety Data Sheet, SDS
Environmental Fact Sheet

Liability statements on:

- Compliance to Food Contact Regulations



Polypropylene
HE125MO

Disclaimer

The information contained herein is to our knowledge accurate and reliable as of the date of publication. Borealis extends no warranties and makes no representations as to the accuracy or completeness of the information contained herein, and assumes no responsibility regarding the consequences of its use or for any printing errors.

Our products are intended for sale to industrial and commercial customers. It is the customer's responsibility to inspect and test our products in order to satisfy himself as to the suitability of the products for the customer's particular purpose. The customer is also responsible for the appropriate, safe and legal use, processing and handling of our products. Nothing herein shall constitute any warranty (express or implied, of merchantability, fitness for a particular purpose, compliance with performance indicators, conformity to samples or models, non-infringement or otherwise), nor is protection from any law or patent to be inferred. No statement herein shall be construed as an endorsement of any product or process.

Insofar as products supplied by Borealis or its subsidiary companies are used in conjunction with third party materials, it is the responsibility of the customer to obtain all necessary information relating to the third party materials and ensure that Borealis' products when used together with these materials are suitable for the customer's particular purpose. No liability can be accepted in respect of the use of Borealis' products in conjunction with other materials. The information contained herein relates exclusively to our products when not used in conjunction with any third party materials.